

# **Kuraray Poval**<sup>™</sup>

## Kuraray Poval <sup>™</sup> 5-88 FA Technical Data Sheet


#### Characteristics

Polyvinyl alcohol which will meet specification for INS No. 1203 by the Joint FAO/WHO Expert Committee on Food Additives (JECFA)

Parameter	Unit	Value	Test method
Loss on drying	Weight %	< 5.0	Kuraray G-SOP
Viscosity	mPa⋅s	4.8 - 5.8	Kuraray G-SOP
рН		5.0 - 6.5	Kuraray G-SOP
Degree of hydrolysis	Mol %	86.5 - 89.0	Kuraray G-SOP
Methanol content	Weight %	< 1.0	Kuraray Method, HS-GC
Methyl acetate content	Weight %	< 1.0	Kuraray Method, HS-GC
Ash content as NA <sub>2</sub> O	Weight %	< 0.37	Kuraray G-SOP
Water insoluble substances	Weight %	< 0.1	Kuraray Method
Lead (Pb) content	Mg/kg (ppm)	< 2.0	ISO Method, atomic absorption analysis

The test methods in use are based on Kuraray methods.

For viscosity measurement Brookfield or falling ball viscometer is used.





# **Kuraray Poval**<sup>™</sup>

## Kuraray Poval <sup>™</sup> 5-88 FA Technical Data Sheet

Refer to the Kuraray Poval <sup>™</sup> webpage for regulatory information

#### Kuraray Europe GmbH

Philipp-Reis-Str. 4 65795 Hattersheim am Main Germany

Phone: +49 69 305 85351

Web: <a href="https://www.kuraray-poval.com/">https://www.kuraray-poval.com/</a>

pva@kuraray.com

